

N° DE TRIM ET INTERNES ROBINETTERIE

TRIM N°	NOMINAL TRIM	TRIM CODE	TIGE ET AUTRES PARTIES INTERNES	DISQUE / COIN	SURFACE DE SIEGE
1	410	F6	410 (13Cr) (200-275 HBN)		
2	304	304	304 (18Cr-8Ni)		
2S	304 HARD FACED	304HFS	304 (18Cr-8Ni)	304 (18Cr-8Ni)	304 (18Cr-8Ni)+ St Gr6
3	310	310	310 (25Cr-20Ni)		
4	410 HARD FACED (HARD F6)	F6H	410 (13Cr) (200-275 HBN)	F6 (13Cr) (200-275 HBN)	F6 (13Cr)
5	410 (F6) FULL HARD FACED	F6HF	410 (13Cr) (200-275 HBN)	HARDFACED - NiCr Alloy	
6	410 (F6) & Cu-Ni	F6HFS	410 (13Cr) (200-275 HBN)	Monel 400®	CA15 ou CuNi
7	410 (F6) HARD F6	F6HF+	410 (13Cr) (200-275 HBN)	F6 (13Cr)	
8	F6 (410) HARD FACED	F6HFS	410 (13Cr) (200-275 HBN)	410 (13Cr)	St Gr6 (CoCr Alloy)
9	Monel	Monel	Monel® (NiCu Alloy)	Monel 400® (NiCu Alloy)	
10	316	316	316 (18Cr-Ni-Mo)		
11	Monel - HARD FACED	MonelHFS	Monel® (NiCu Alloy)	Monel 400® (NiCu Alloy)	Monel 400® + St Gr6
12	316 HARD FACED	316HFS	316 (Cr Ni-Mo)	316 + St Gr6	
13	Alloy 20	Alloy20	Alloy 20 (19Cr-29Ni)		
14	Alloy 20 HARD FACED	Alloy20HFS	Alloy 20 (19Cr-29Ni)	Alloy 20 (19Cr-29Ni) + St Gr6	
15	304 FULL HARD FACED	304HF	304 HF (18Cr-Ni)	304 + St Gr6	
16	316 FULL HARD FACED	316HF	316 HF (18Cr-Ni-Mo)	316 + St Gr6	
17	347 FULL HARD FACED	347HF	347 HF (18Cr-10nl-Cb)	347 + St Gr6	
18	Alloy 20 FULL ARD FACED	Alloy 20HF	Alloy 20 (19Cr-29Ni)	Alloy 20 + St Gr6	